



RE-COAT



DESIGNED TO RESURFACE ALMOST ANY CONCRETE SURFACE

RE-COAT is a single component, high performance, polymer modified topping mix designed to resurface almost any concrete surface. RE-COAT can be used on horizontal or vertical surfaces and can be pigmented which eliminated the need for painting. RE-COAT can protect, restore and color most concrete, asphalt and wood surfaces without changing the appearance or texture.

PRODUCT HIGHLIGHTS

- Superior Adhesion, Scratch resistant, Weather resistant
- Can be stained with EZChem Enviro Stain or Earthtone Stain for a wide array of decorative finishes.
- Can be sealed with EZChem Clear Acrylic Sealer or Colored Acrylic Sealer for a consistently colored and durable surface.
- Easy to use and apply
- Durable Cement Finish

USES

- Can be used over interior or exterior, horizontal and vertical concrete surfaces that are structurally sound and properly prepared.
- **RE-COAT** is used for resurfacing, reviving, protecting and coloring surfaces such as driveways, walkways, pool decks, brick pavers, walls and precast concrete structures as well as other use
- **RE-COAT** sets to a rock hard surface that resists water penetration and provides a durable and beautiful textured surface.

QUICK LOOK:

Compressive Strength:	28 days Air Cure	4523 psi
Tensile Strength:	28 Days Air Cure	680 psi
Flexural Strength:	28Days Air Cure	1835 psi
Impact Strength:	28 Days Air Cure	16
Abrasion Resistance:		
% Weigh Loss	28 Days Air Cure	1.15
Shear Bond:	28 Day Air Cure	1835
Coverage: (Approximately)		
1000 sq.ft. at 3mil		
400 sq.ft. at 5 mil		



Application Temperature: 50°-100°F
Cured: 28 days

FOR MORE INFORMATION,
PLEASE SEE SDS.

Manufactured In The USA By



*Product warranty for one year from date of manufacture
For more information on EZChem and all products manufactured by EZChem please visit our website: www.ezchemusa.com



RE-COAT

SURFACE PREPARATION:

The surface must be clean and free from all sealers, paints, grease, oil or any other contaminants. Use CITRA PRO to degrease the surface if necessary and SUPER BLUE to wash the concrete surface. Using a pressure washer completely wash the surface, making sure to rinse the surface thoroughly making it clean of all debris and contaminants. Allow the surface to dry completely before applying RE-COAT.

HOW TO USE:

One bag of RE-COAT will use approximately 7 quarts of water. For best results use a 1/2 inch drill with a jiffy type mixing paddle. Add the measured water to a clean 5 gallon pail. Add Two EZ COLOR PAK pigments to your measured water, if desired, and mix in. With the mixer running slowly, add the RE-COAT mixing until a lump free consistency is obtained (about 2 minutes) After mixing, the product should be the consistency of thick paint. Allow the mixed product to set, or slake for approximately 5 minutes and then re-mix for 1 minute prior to placement. If needed, up to 1 quart of water can be added to get to desired consistency. RE-COAT has a pot life of about 2 hrs. Remix if necessary to freshen up, adding a dash of water if needed. Lightly mist the surface with cool, clean water. Do Not Puddle. If using a roller, use a 3/8 or larger nap. Apply RE-COAT making sure to get an even application without roller marks. If using a sprayer, apply at 15-20 PSI with the smallest tip (1-15mm)

PRECAUTIONARY STATEMENT:

Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Avoid breathing dust/fume/gas/mist/vapours/spray. Wash hands thoroughly after handling. Do not eat, drink or smoke when using this product. Wear protective gloves/protective clothing/eye protection/face protection. Take off contaminated clothing and wash before reuse. Store in a well-ventilated place. Keep container tightly closed. Store locked up. Dispose of contents/container to approved waste disposal site.

FIRST AID:

INHALATION: Move to fresh air to avoid nuisance symptoms.

SKIN CONTACT: Wash affected area thoroughly with soap and water. Rinse well. If irritation develops Get Medical Help.

EYE CONTACT: Rinse thoroughly with water for 15 minutes, lifting both eyelids. If irritation persists, Get Medical Help.

INGESTION: Rinse mouth with water. Drink 2 glasses of water to dilute. Do not induce vomiting. Get Immediate Medical Help. Never give anything by mouth to an unconscious person.

IN CASE OF FIRE:

This product is not flammable.

FOR EMERGENCY HELP

24 Hours a Day contact:

INFOTRAC at 1-800-535-5053