



GFX - GLASS SERIES (VRM)

PRODUCT DESCRIPTION

GFX GLASS SERIES (VRM) is a 100% solid, two component epoxy coating, designed for controlling the moisture vapor emission rate on deteriorated or new floors. The ASTM F3010 product requirements for vapor permeance are met when applied at a thickness of 18 mils. The coating will control moisture vapor emission rates up to 25 lb. /24 hr. /1000 square feet. Providing excellent resistance to abrasion and chemical resistance, it meets many requirements such as durability, performance as well as aesthetics.

APPLICATIONS

GFX GLASS SERIES (VRM) is formulated as a high solids system for cleanrooms, laboratories, walkways, areas of light manufacturing, and where cleanliness and easy maintenance are required.

ADVANTAGES

- Solvent-free, Low VOC content
- 100% solids with an esthetic high gloss finish
- Superior mechanical resistance
- Good chemical and physical resistance
- Easy to clean, bacteria and moisture resistant surface

PACKAGING

GFX GLASS SERIES (VRM) is packaged in factory proportioned packaging for easy handling and mixing.

Resin (R): 2 US gallons

Hardener (H): 1 US gallon

STORAGE

All components should be stored in dry, temperature controlled areas between 12-28°C. Do not expose to freezing or excessive high heat.

TECHNICAL DATA			
PERCENT SOLIDS	100%	POT LIFE	50-60 minutes
VOC CONTENT	41.77 (g/L)	MIXING RATIO	2:1
# OF COATS	2	RECOAT TIME	8-24 hours
SHELF LIFE	12 months		
MATERIAL PROPERTIES			
COMPRESSIVE STRENGTH ASTM D695	6800 psi		
BOND RESISTANCE ASTM D4541	268 psi		
TENSILE STRENGTH ASTM D638	5500 psi		
ABRASION RESISTANCE ASTM D4060 (CS17/1000 CYCLES/1000G)	0.10 gram		
PERMEABILITY (%) ASTM D570	0.3		
HARDNESS (SHORE D) ASTM 2240	85-90		



GFX - GLASS SERIES (VRM)

SURFACE PREPARATION

Surface must be clean, sound and dry. Prior to coating a floor all trowel marks and surface imperfections must be removed to produce a smooth & uniform surface. Proper surface preparation is critical to ensure an adequate chemical bond to substrate. Substrate must be dry and free of all wax, grease, oils, fats, soil, contaminants, loose or foreign matter and laitance. Concrete should be cleaned and prepared using a shot blast machine or adequate grinding equipment to achieve a CSP-3 to CSP-4 profile as per ICRI guidelines. Compressive strength of concrete should be at least 3,500 psi (24 Mpa) @ 28 days and at least 215 psi (1.5 Mpa) in tension at time of product application.

MIXING

GFX GLASS SERIES (VRM) is supplied in factory proportioned quantities, greatly reducing the risk of applicator error during mixing.

Step 1 - Mechanically premix PART A (resin) with an appropriate slow speed drill equipped with a Jiffy Mixer, for 1 minute.

Step 2 - Slowly empty entire content of PART B into container holding PART A and continue to mix slowly for 3 minutes until uniform consistency in texture and color is achieved. Avoid unnecessary entrapment of air during mixing. Make sure to scrape walls and bottom of container with straight edged trowel at least once to ensure homogeneous mix. Make sure to empty ALL contents of PART B into PART A to avoid system weakening or incomplete curing.

DO NOT MIX MORE MATERIAL THAN CAN BE APPLIED WITHIN WORKING TIME LIMITS.

POT LIFE

After mixing, the pot life is approximately 50-60 minutes at 25°C. Pot life depends on ambient and surface conditions.

APPLICATION

GFX GLASS SERIES (VRM) should be applied at ambient and surface temperatures between 15-28°C and humidity below 80%. This coating is applied with a rubber squeegee and back rolled with a 10mm lint-free nap roller (on smooth surfaces) to remove squeegee lines and smooth out coating. Additional coats may be applied when surface is tack-free (roughly 8 hours). Do not exceed first 24 post-application hours for recoating. By exceeding this 24 hour recoat time limit, the entire surface must be lightly sanded to achieve desired profile for a proper mechanical bond. Clean up all dust and debris created by aforementioned sanding prior to applying subsequent coat.

CURING

GFX GLASS SERIES (VRM) is tack-free in approximately 8 hours at 25°C. Coated area may be put back into service after 24 hours. Curing is complete and full product characteristics are achieved after 10 days. Curing times dependent upon ambient & surface conditions.

PRECAUTIONS AND LIMITATIONS

Prior to application, measure and confirm Substrate Moisture Content, Ambient and Surface temperatures and Dew Point.

Substrate Moisture: Moisture within substrate must be $\leq 4\%$ by mass as measured by Tramex® type concrete moisture meter on mechanically prepared surface.



GFX - GLASS SERIES (VRM)

Dew Point: AVOID CONDENSATION. The substrate must be at least 3°C above Dew Point to reduce risk of condensation. Condensation may lead to failure in adhesion. Avoid situations where substrate temperature is considerably lower than ambient temperature.

Do not add thinners or solvents to mix. Do not add water. Dispose of waste materials in accordance with government regulations. The use of safety glasses and protective gloves is required. In case of contact, flush areas with abundance of water for 20 minutes and seek medical assistance. Wash skin with soap and water. Use only in well ventilated areas.